

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
27 September 2001 (27.09.2001)

PCT

(10) International Publication Number  
**WO 01/70824 A2**

- (51) International Patent Classification<sup>7</sup>: C08F 2/00 (74) Agents: JOHNSON, Philip, S. et al.; Johnson & Johnson, One Johnson and Johnson Plaza, New Brunswick, NJ 08933 (US).
- (21) International Application Number: PCT/US01/09076
- (22) International Filing Date: 22 March 2001 (22.03.2001) (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
09/532,234 22 March 2000 (22.03.2000) US
- (71) Applicant: JOHNSON & JOHNSON VISION CARE, INC. [US/US]; 7500 Centurian Parkway, Suite 100, Jacksonville, FL 32256 (US).
- (72) Inventors: VANDERLAAN, Douglas, G.; 8114 Parkridge Circle South, Jacksonville, FL 32211 (US). LOVE, Robert, N.; 1748 El Camino Road, Apartment 3, Jacksonville, FL 32216 (US). FORD, James, D.; 515 Nassau Court, Orange Park, FL 32003 (US). ALLI, Azaam; 7816 Southside Blvd., Apartment 221, Jacksonville, FL 32256 (US). WOOD, Joe, M.; 1888 Edgewood Avenue South, Jacksonville, FL 32205 (US). NUNEZ, Ivan, M.; 5934 Bridlewood Drive SW, Roanoke, VA 24018 (US).
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 01/70824 A2

(54) Title: STABLE INITIATOR SYSTEM

(57) Abstract: Acylphosphine initiators used in making ophthalmic lenses are stabilized by the addition of an acid to the monomer mix used to make the lenses.

## STABLE INITIATOR SYSTEM

### Background of the Invention

This invention relates to the use of photoinitiators. More particularly, it relates  
5 to the stabilization of photoinitiators useful in processes for making ophthalmic lenses.

Ophthalmic lenses such as contact lenses are often made in processes that employ photoinitiated polymerization reactions. UV and visible radiation are most frequently used to initiate cure in these reactions. It is often desirable to prepare a  
10 mixture of materials together with an initiator or initiator system (where initiation involves more than one component) and other additives that will ultimately form the lens upon completion of the reactions. These types of mixtures are referred to as the "monomer mix" in this context. Stability of the initiator can be a crucial factor in the working time and shelf life of the monomer mix. Increasing the working time of  
15 the monomer mix is desirable since it reduces the need for preparation of starting materials and the possibility of introducing lot to lot and intra-lot variations in lens production.

Acylophosphines are an interesting and useful class of initiators for free radical polymerizations of the type frequently used to make ophthalmic lenses. Reaction  
20 mechanisms for many of these materials are described in *Reaction Mechanism of Monoacyl- and Bisacylphosphine Oxide Photoinitiators Studied by  $^{31}\text{P}$ ,  $^{13}\text{C}$ -, and  $^1\text{H}$ -CIDNP and ESR*, Urszula Kolczak, Gunther Rist, Kurt Dietliker, and Jacob Wirz, 118 J. Am. Chem. Soc., 6477 (1996). Bisacylphosphines and their use are further described in US Patent 5,534,559 and JP-A-8-259642 incorporated herein by  
25 reference.

Unfortunately, this class of compounds tends to be unstable in a variety of environments lessening its potential as an active initiator. EP 849,296 proposes a method of stabilizing bisacylphosphine initiators used in the production of urethane (meth)acrylate polymers used for coatings. The method involves combining the  
30 monomer components together with the initiator in the presence of a tertiary amine and in the absence of a tin component. Japanese patents JP-A-4-6125; JP-A-

296315; JP-A8-127630 propose similar methods of stabilizing monoacylphosphine photoinitiators in the presence of a tin compound used as a polymerization catalyst.

Unfortunately, these solutions are not desirable when applied to monomer mixes used to make ophthalmic lenses because of the potentially deleterious effect they may have on various components of the monomer mix. This is particularly true where the monomer mix is used to make silicone hydrogel lenses.

A new method for stabilizing acylphosphine initiators is desirable.

### Summary of the Invention

The invention is a stable monomer mix for making ophthalmic lenses. The stable monomer mix is made by admixing a monomer mixture, an initiator, and an acid.


In another aspect of the invention a silicone hydrogel monomer formulation is made by admixing a silicone hydrogel forming mixture, an initiator, and an acid.

In yet another aspect of the invention, a method of stabilizing an initiator system comprises lowering the pH of the initiator system.

In yet another aspect of the invention, a process for stabilizing a silicone hydrogel monomer formulation in an admixture of a reactive silicone macromer and a photoinitiator comprises admixing an acid with the admixture of macromer and photoinitiator.


### Detailed Description of the Invention

The initiators of this invention are those having the following structure:



Structure I

wherein,  $R^1$ ,  $R^2$ , and  $R^3$  are each independently H or a  $C_{1-12}$  substituted or unsubstituted alkyl, cycloalkyl, or aromatic moiety provided that at least one of  $R^1$ ,  $R^2$  and  $R^3$  has the following structure:



5

#### Structure II

and is attached to the P at the acyl carbon, and wherein,  $R^4$ - $R^8$  are independently, H  
10 or a  $C_{1-3}$  substituted or unsubstituted alkyl or alkoxy moiety.

In each case, where an  $R^1$ - $R^8$  group is substituted, the substituent can comprise a hydroxy or  $C_{1-4}$  alkyl, alkoxy, alkenyl, or alkynyl group. Substitution with hetero atoms such as nitrogen, sulfur, and halo atoms is possible but is not favored.


15

It is preferred that  $R^1$  and  $R^2$  are both Structure II moieties with  $R^4$  and  $R^8$  substituents. It is most preferred that  $R^4$  and  $R^8$  are methoxy groups. It is further preferred in this embodiment that  $R^3$  is a  $C_{1-10}$  alkyl, alkoxy, or alkenyl group substituted with  $C_{1-2}$  alkyl groups; most preferably a substituted pentyl group.

20

In the most preferred embodiment,  $R^1$  and  $R^2$  are both Structure II moieties with  $R^4$  and  $R^8$  being methoxy groups;  $R^1$  is a trimethyl pentyl group. Thus, the most preferred embodiment has the following structure:

25



Structure III

Theses initiators can be used alone or in combination with other initiators  
 5 such as benzoin methyl ether, 1-hydroxycyclohexyl phenyl ketone, Irgacure 1850  
 brand photoinitiator, 1-hydroxy cyclohexyl phenyl ketone (commercially available  
 as "Irgacure 184"); 2-benzyl-2-n-dimethylamino-1-(4- morpholinophenyl)-i-  
 butanone (commercially available as "Irgacure 369"); 1- hydroxycyclohexyl phenyl  
 ketone (50% by weight) plus benzophenone (commercially available as "Irgacure  
 10 500"); 4-(2- hydroxyethoxy) phenyl-(2-hydroxy propyl)ketone (commercially  
 available as "Irgacure 2959"); 2,4,6-Trimethyl benzoyl diphenyl phosphineoxide  
 (TPO) (50% by weight) plus 2-hydroxy-2-methyl-1-phenyl-propan-1-one  
 (HMPP) (50% by weight) (commercially available as "Darocur 4265"); 2,2-  
 dimethoxy-2- phenylacetophenone (BDK) (commercially available as "Irgacure  
 15 651"); bis (nl-2,4- cyclopentadien-1-yl), bis (2,6-difluoro-3-(1H-pyrrol-1-  
 yl)phenyl) Titanium (CGI-784); 2-methyl-1-(4- (methylthio)phenyl)-2-morpholino  
 propan-1-one (MMMP) (commercially available as "Irgacure 907"); 2-hydroxy-2-  
 methyl-1-phenyl-propan-1-one (HMPP) (commercially available as "Darocur  
 1173"); or mixtures thereof. Mixtures that include a UV and visible light initiator  
 20 system are preferred as they permit more flexible use of UV blockers in the  
 monomer mix.

The stabilizers useful in this invention are acids. These are preferably weak  
 organic acids but may include strong inorganic acids as well as Lewis acids.  
 Additionally, precursors capable of generating acids in the reaction mixture can  
 25 also be used. The most preferred acids are acetic acid, formic acid, propionic acid,  
 and acrylic acid.

The inorganic acids include, for example, hydrochloric acid, hydrobromic acid, sulfuric acid, phosphoric acid, hydroiodic acid, hydrofluoric acid, sulfurous acid, nitric acid, nitrous acid, phosphorous acid, perchloric acid, chloric acid, chlorous acid, iodic acid, bromic acid, arsenic acid, carbonic acid, selenium  
5 hydride, tellurium hydride, phosphonic acid, hypophosphoric acid, diphosphonic acid, pyrophosphoric acid, metaphosphoric acid, polyphosphoric acid, selenic acid, selenious acid, telluric acid, tellurous acid, arsenious acid, antimononic acid, antimonous acid, borofluoric acid, etc.

The organic acids include, for example, the sulfonic acids such as  
10 hydroxymethanesulfonic acid, trifluoromethanesulfonic acid, beta-bromoethanesulfonic acid, allylsulfonic acid, 2-methyl-2-[(1-oxo-2-propenyl)amino]-1-propanesulfonic acid, D-10-camphorsulfonic acid, benzenesulfonic acid, m-nitrobenzenesulfonic acid, m-benzenedisulfonic acid, methanesulfonic acid, ethanesulfonic acid, 2-hydroxyethanesulfonic acid, 2-  
15 (cyclohexenylamino)methanesulfonic acid, (3-cyclohexenylamino)methanesulfonic acid, p-ethylbenzenesulfonic acid, alpha-naphthalenesulfonic acid, beta-naphthalenesulfonic acid, p-toluenesulfonic acid, p-chloromethylbenzenesulfonic acid, p-phenolsulfonic acid, 2-pyridylhydroxymethanesulfonic acid, 2,6-naphthalenedisulfonic acid, etc.; the  
20 organic sulfinic acids such as benzenesulfinic acid, p-toluenesulfinic acid, etc.; the organic phosphoric acids such as phenylphosphonous acid, butylphosphonous acid, methylphosphonous acid, dibenzenephosphinic acid, dibutylphosphinic acid, benzenephosphonic acid, methylphosphonic acid, phenylphosphinic acid, methylphosphinic acid, dibenzenethiophosphinic acid, dibutylthiophosphinic acid, benzenethiophosphonic acid, methylthiophosphonic  
25 acid, phenylthiophosphinic acid, methylthiophosphinic acid, benzenethiophosphonous acid, dibutylthiophosphonous acid, diethyl dithiophosphate, alpha-hydroxybenzylphosphonous acid, toluenephosphonous acid, etc.; the substituted or non-substituted aliphatic carboxylic acids include for  
30 example mandelic acid, acetic acid, lactic acid, ascorbic acid, phenylacetic acid, bromoacetic acid, trichloroacetic acid, chlorodifluoroacetic acid, thioacetic acid, glycolacetic acid, glyoxylic acid, acrylic acid, beta-chloroacrylic acid, cyanoacetic

acid, ethoxyacetic acid, beta -chloropropionic acid, perfluoropropionic acid,  
 propiolic acid, n-butyric acid, isobutyric acid, alpha -hydroxyisobutyric acid,  
 crotonic acid, mucochloric acid, cyclopropanecarboxylic acid, isovaleric acid, 1-  
 methylcyclopropanecarboxylic acid, 1-cyanocyclopropanecarboxylic acid,  
 5 cyclobutanecarboxylic acid, cyclopentanecarboxylic acid, 2-ketobutyric acid,  
 levulinic acid, pivalic acid, tert-butylacetic acid, coumarinic acid, 3-  
 cyclohexenecarboxylic acid, beta-2-furylacrylic acid, 3-pyridylacetic acid,  
 phenylthioacetic acid, m-chlorophenylacetic acid, o-nitrophenylacetic acid, p-  
 fluorophenylacetic acid, o-hydroxyphenylacetic acid, phenoxyacetic acid, o-  
 10 chlorophenoxyacetic acid, 2,4-dichlorophenoxyacetic acid, 2,4,5-  
 richlorophenoxyacetic acid, cyclohexylacetic acid, 1-methyl-1-  
 cyclohexanecarboxylic acid, 6-acetamidohexanoic acid, heptylic acid, dl-terebic  
 acid, benzoylformic acid, cinnamic acid, o-chlorocinnamic acid, 2,4-  
 dichlorocinnamic acid, m-nitrocinnamic acid, o-hydroxycinnamic acid, d -2-  
 15 phenoxypropionic acid, 3-phenoxypropionic acid, 3-phenylpropionic acid, 3-(p-  
 hydroxyphenyl)propionic acid, 2-(2,4,5-trichlorophenoxy)propionic acid, 4-  
 methoxyphenylacetic acid, p-chloro-2-methylphenylacetic acid, 3,4-  
 methylenedioxyphenylacetic acid, 4-chloro-2-methylphenoxyacetic acid, m-  
 tolylacetic acid, alpha , alpha , alpha-trifluoro-m-tolylacetic acid, p-  
 20 hydroxyphenylpyruvic acid, alpha -cyanocinnamic acid, p-methoxycinnamic acid,  
 m-trifluoromethylcinnamic acid, 3,4-methylenedioxcinnamic acid 3,4-  
 dimethoxyphenylacetic acid, ( - )- alpha-methoxy- alpha -  
 trifluoromethylphenylacetic acid, 1,4-benzdioxane-6-acetic acid, 3-phenyl-n-  
 butyric acid, 1-phenyl-1-cyclopropanecarboxylic acid, 2-(p-methoxyphenyl)-  
 25 acetylene-1-carboxylic acid, 3-benzoylpropionic acid, 2-(p-chlorophenoxy)-2-  
 methylpropionic acid, alpha -naphthylacetic acid, beta-naphthoxyacetic acid,  
 3,4,5-trimethoxyphenylacetic acid, diphenylacetic acid, bis(p-chlorophenyl)acetic  
 acid, 1-menthoxyacetic acid, diphenyleneacetic acid, 1-  
 phenylcyclopentanecarboxylic acid, 1-(p-chlorophenyl)-1-cyclopentanecarboxylic  
 30 acid, dl-3-camphorcarboxylic acid, palmitic acid, stearic acid, benzilic acid,  
 desoxycholic acid, linolic acid, oleic acid, alpha -acetamidocinnamic acid, etc.; the  
 aromatic carboxylic acids include for example benzoic acid, salicylic acid, o-toluic

acid, alpha , alpha , alpha -trifluoro-m-toluic acid, p-ethylbenzoic acid, 2,6-dimethylbenzoic acid, 2,4,6-trimethylbenzoic acid, p-tertbutylbenzoic acid, p-bromomethylbenzoic acid, 2-biphenylcarboxylic acid, 4,4'-methylenebis(3-hydroxy- beta -naphthoic acid), alpha -naphthoic acid, p-benzoylbenzoic acid,

5 phthalamic acid, o-phthalaldehydic acid, m-nitrobenzoic acid, 3,4-dinitrobenzoic acid, m-cyanobenzoic acid, thiosalicylic acid, gallic acid, m-hydroxybenzoic acid, 2,3-dihydroxybenzoic acid, 1-hydroxy-2-naphthoic acid, o-anisic acid, 3,4-dimethoxybenzoic acid, 4-hydroxy-3-methoxybenzoic acid, 4-hydroxy-3,5-dimethoxybenzoic acid, 4-n-butoxybenzoic acid, 3-phenoxybenzoic acid,

10 piperonylic acid, o-acetamidobenzoic acid, p-chlorobenzoic acid, 3,5-dichlorobenzoic acid, o-fluorobenzoic acid, m-fluorobenzoic acid, 2,6-difluorobenzoic acid, 2,6-dichlorobenzoic acid, 2,3,5-triiodobenzoic acid, 4-chlorosalicylic acid, 3-nitrosalicylic acid, 5-bromosalicylic acid, 2-chloro-3-nitrobenzoic acid, 3-chloro-4-hydroxybenzoic acid, 3,5-dichloro-4-

15 hydroxybenzoic acid, 3-chloro-4-methylbenzoic acid, 3-methoxy-4-nitrobenzoic acid, 3-methoxy-4-hydroxybenzoic acid, 3-methoxy-4-methylbenzoic acid, 3-methyl-2-nitrobenzoic acid, 3-hydroxy-4-nitrobenzoic acid, 3,5-di-tert-butyl-4-hydroxybenzoic acid, o-thymotinic acid, etc.; the heteroaromatic carboxylic acids include for example N-methylpyrrole-2-carboxylic acid, 2-furancarboxylic acid, 5-

20 bromo-2-furancarboxylic acid, pyrrole-2-carboxylic acid, 3-furancarboxylic acid, nicotinic acid, isonicotinic acid, citrazinic acid, alpha -picolinic acid, etc.; the substituted or non-substituted aliphatic polyhydric carboxylic acids include for example succinic acid, fumaric acid, maleic acid, malic acid, tartaric acid, citric acid, oxalic acid, malonic acid, ethylmalonic acid, hydroxymalonic acid,

25 methylsuccinic acid, 2-methyl-2-phenylsuccinic acid, 2-ethyl-2-methylsuccinic acid, 2-isopropylsuccinic acid, bromosuccinic acid, 2,3-dibromosuccinic acid, alpha -ketoglutaric acid, 3-ethyl-3-methylglutaric acid, glutaconic acid, itaconic acid, mesaconic acid, citraconic acid, adipic acid, camphoric acid, diglycollic acid, acetylenedicarboxylic acid, dimethylcyclopropanedicarboxylic acid, etc.; the

30 aromatic dicarboxylic acids include for example phthalic acid, isophthalic acid, terephthalic acid, homophthalic acid, 3-nitrophthalic acid, 4-hydroxyisophthalic acid, tetrachlorophthalic acid tetrachloroterephthalic acid, nitroterephthalic acid,



pyrazine-2,3-dicarboxylic acid, o-phenylenediacetic acid, 5,5'-methylenedisalicylic acid, etc.; the phenols include for example picric acid, 2,4-dinitrophenol, 2,6-dinitrophenol, 2,6-diiodo-4-nitrophenol, 2,6-dichloro-4-nitrophenol, 2,5-dichloro-4-nitrophenol, 2,6-dibromo-4-nitrophenol, 2-bromo-4-chloro-6-nitrophenol, 2,4-dichloro-6-nitrophenol, etc.; and the substituted or non-substituted dithiocarbamic acids include for example 2-cyclohexenyldithiocarbamic acid, 2-cycloheptenyldithiocarbamic acid, methylthiocarbamic acid, dimethylthiocarbamic acid, ethylenebis(dithiocarbamic acid), etc.

10 Lewis acids include, for example, boron trifluoride, boron trichloride, boron tribromide, aluminum fluoride, aluminum chloride, aluminum bromide, aluminum iodide, aluminum sulfate, iron fluoride, iron chloride, iron bromide, iron nitrate, iron sulfate, gallium fluoride, gallium chloride, antimony fluoride, antimony chloride, antimony sulfate, indium fluoride, indium chloride, tin  
15 fluoride, tin chloride, tin bromide, tin iodide, arsenic fluoride, arsenic chloride, zinc fluoride, zinc chloride, zinc bromide, zinc iodide, copper chloride, barium chloride, silver chloride, etc.

It is generally desirable that acids used in the practice of this invention are of such molarity or concentration that they imbue the monomer mix in which they are to be used with a pH of 3 to 8. Preferably, it is less than 7. While the upper  
20 end of the pH scale to which the monomer mix could be lowered is slightly alkaline, the addition of acid lowers the pH to point that it would not otherwise reside. In any event, in the case of a monoprotic acid such as HCL, about 0.1 to about 10 weight % of acid is used in the monomer mix. Based on this, the skilled  
25 artisan can readily determine equivalent ranges for other acids useful in the practice of this invention.

Making the lenses of this invention is conducted by combining the components of the monomer mix together with the initiators and stabilizers described above according to well known methods of lens formation such as  
30 photoinitiated casting in lens molds.

Silicone hydrogels have high oxygen permeability making them particularly desirable for use in the lenses of this invention. When the monomer mix


comprises components for the preparation of silicone hydrogels, it is referred to herein as a silicone hydrogel forming mixture. Silicone hydrogels are preferably prepared by polymerizing a mixture containing at least one silicone-containing monomer and at least one hydrophilic monomer. Either the silicone-containing monomer or the hydrophilic monomer may function as a crosslinking agent or a separate crosslinker may be employed. Crosslinking agents are monomers having multiple polymerizable moieties. The term "monomer" when used in this sense refers to a material used in forming the ultimate polymer system. The crosslinking agent can be monomeric, dimeric, trimeric, or polymeric molecules and still be considered a monomer with respect to the silicone hydrogel ultimately produced from it. The polymerizable functionalities generally bond to more than one polymer chain creating a network or network-like polymeric structure. There are numerous silicone-containing monomeric units commonly used in the formation of silicone hydrogels. U.S. Pat. Nos. 4,136,250; 4,153,641; 4,740,533; 5,034,461; 5,070,215; 5,260,000; 5,310,779; and 5,358,995 provide some useful examples and each is incorporated herein by reference.

Hydrophilic monomers that have previously been found useful for making silicone hydrogels include: unsaturated carboxylic acids, such as methacrylic and acrylic acids; acrylic substituted alcohols, such as 2-hydroxyethylmethacrylate and 2-hydroxyethylacrylate; vinyl lactams, such as N-vinyl pyrrolidone; and acrylamides, such as methacrylamide and N,N-dimethylacrylamide. Still further examples are the hydrophilic vinyl carbonate or vinyl carbamate monomers disclosed in U.S. Pat. Nos. 5,070,215, and the hydrophilic oxazolone monomers disclosed in U.S. Pat. No. 4,910,277 and each is incorporated herein by reference.

The preferred components of the monomer mix used to make the silicone hydrogel lenses of this invention include, for example, siloxanes and acrylic/methacrylic acid and derivatives, polyvinyl, typically di- or tri-vinyl monomers, such as di- or tri(meth)acrylates of diethyleneglycol, triethyleneglycol, butyleneglycol and hexane-1,6- diol; divinylbenzene. In the preferred embodiment, the siloxane component is a polydimethyl siloxane. It is combined with a hydrophilic monomer such as hydroxyethyl methacrylate or acrylate derivative. In the most preferred embodiment, the monomers comprise mono-alkyl terminated

polydimethylsiloxanes ("mPDMS") such as monomethacryloxy propyl terminated polydimethyl siloxane and a macromer comprising the reaction product of 2-hydroxyethyl methacrylate, methyl methacrylate, methacryloxypropyltris(trimethylsiloxy)silane, mono-methacryloxypropyl terminated mono-butyl terminated polydimethylsiloxane, and 3-isopropenyl- $\alpha,\alpha$ -dimethylbenzyl isocyanate. Additionally preferred monomers include, for example, methacryloxypropyl tris(trimethyl siloxy) silane, "TRIS"; N,N-dimethyl acrylamide, "DMA"; triethyleneglycoldimethacrylate, "TEGDMA". Other monomers and crosslinking agents known in the art for making silicone hydrogels can also be used.

The employment of mPDMS is noteworthy as it is thought to be responsible for imbuing the resulting hydrogel with improved mechanical properties such as reduced elastic modulus and  $\tan \delta$  (loss modulus of the material divided by its elastic modulus or  $G''/G'$ ) without compromising monomer compatibility during the polymerization process. Unlike many of the siloxanes predominantly used at present, mPDMS has no polar functionality and is of relatively high molecular weight. Measures to improve its incorporation are thus welcome. The structure of mPDMS can be described as follows:



20

where  $b = 0$  to  $100$ , and  $R_{57}$  is any  $C_{1-10}$  aliphatic or aromatic group which may include hetero atoms; provided that  $R_{57}$  is not functionalized at the point at which it is bonded to Si.  $C_{3-8}$  alkyl groups are preferred with butyl groups, particularly sec-butyl groups, being most preferred.  $R_{56}$  is any single polymerizable vinyl group. Preferably it is a methacryl moiety but it can also be an acryl or styrenic moiety or other similar moiety.

The monomer mix also includes the initiators and acids described above. These can be added to the mix before, during, or after the mix is combined in a lens mold or other vessel for lens formation.

It is also desirable to carry out the cure in the presence of a diluent. Suitable diluents include alkanols, N,N- dimethylformamide acetamide, acetonitrile, N,N- dimethylacetamide, heptane, dimethyl sulfoxide, acetone, tert-butyl acetate, ethyl acetate, isopropyl acetate, and N-methyl-2-pyrrolidone. Low molecular weight ( $C_{5-12}$ ) alkanols are preferred. Dimethyl-3-octanol is most preferred.

The invention is further described in the following nonlimiting examples.

10

#### **Example 1 (Macromer Formation)**

To a solution of 13.75 ml of a 1M solution of TBACB in THF, 30.0g bis(dimethylamino)methylsilane, 61.39 g p-xylene, 154.28 g methyl methacrylate, and 1892.13 g 2-(trimethylsiloxy)ethyl methacrylate in 4399.78 g THF at 14°C, under a  $N_2$  atmosphere, was added 191.75 g of 1-trimethylsiloxy-1-methoxy-2-methylpropene. 30 ml of additional TBACB in THF (0.40 M) was added over a period of 260 minutes, during which time the reaction mixture was allowed to exotherm, and then cooled to 30°C. Sixty minutes after addition of 2-(trimethylsiloxy)ethyl methacrylate, A solution of 467.56 g 2-(trimethylsiloxy)ethyl methacrylate, 3636.6 g mPDMS and 3673.84 g TRIS and 20.0 g bis(dimethylamino)methylsilane was added, and the mixture was allowed to exotherm and then cooled to 30°C for 2 hours. A solution of 10.0g bis(dimethylamino)methylsilane, 154.26 g methyl methacrylate, and 1892.13 g 2-(trimethylsiloxy)ethyl methacrylate was then added and the mixture was again allowed to exotherm. After 2 hours, 2 gallons of anhydrous THF was added, followed by a solution of 439.69 g water, 740.6 g methanol and 8.8 g dichloroacetic acid after the solution was allowed to cool down to 34°C. The mixture was refluxed for 4.5 hours, heating with an oil bath at 110°C, and volatiles were distilled off at 135°C, with addition of toluene to aid in removal of water, until a vapor temperature of 110°C was reached.

30

The reaction flask was cooled to 110°C, and a solution of 443 g TMI and 5.7 g dibutyltin dilaurate was added. The mixture was reacted for 3.5 hours, then cooled

to 30°C. The toluene was evaporated under reduced pressure to yield off-white, anhydrous, waxy, reactive macromer. The theoretical OH content of the macromer is 1.69 mmol/g.

5

### Example 2 (Lens Formation)

A hydrogel was made from the following monomer mix (all amounts are calculated as weight percent of the total weight of the combination): macromer of example 1 (~18%); an Si<sub>7,9</sub> monomethacryloxy terminated polydimethyl siloxane (~28%); methacryloxypropyl tris(trimethyl siloxy) silane, "TRIS" (~14%); dimethyl amide, "DMA" (~26%); hydroxy ethyl methacrylic acid, "HEMA" (~5%); triethyleneglycoldimethacrylate, "TEGDMA" (~1%), polyvinylpyrrolidone, "PVP" (~5%); CGI 1850 (a 1:1 (wgt) blend of 1-hydroxycyclohexyl phenyl ketone and bis(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentyl phosphine oxide) photoinitiator 15 (~1%), glacial acetic acid (~5%), with the balance comprising minor amounts of additives. The polymerization was conducted in the presence of 20%wt dimethyl-3-octanol diluent.

The hydrogels were formed by adding about 0.10 g of the monomer mix to 20 the cavity of an eight cavity lens mold of the type described in U.S. Patent 4,640,489 and curing for 1200 sec. Polymerization occurred under a nitrogen purge and was photoinitiated with 5 mW cm<sup>-2</sup> of UV light generated with an Andover Corp. 420PS10-25 AM39565-02 light filter.

Lenses were successfully made from this monomer mix over the course of 5 25 days without reconstitution of the macromer or other components of the monomer mix.

This example illustrates the lengthy working time that can be attained by stabilizing the initiator according to this invention.

30

**Example 3 (Comparative- No Acid)**

Example 2 was repeated except that no acetic acid was included in the monomer mix. Lenses could only be made for 10 hours before the monomer mix required reconstitution due to loss of activity of the initiator.

5

**Examples 4-8 (Stability Studies)**

Solutions containing 0.8 %wt of CGI 1850, and various reagents were prepared in a diluent, 3-methyl-3-pentanol. Samples were analyzed by Reversed-phase high performance liquid chromatography with Uv-Vis detection, to  
 10 determine the presence of DMBAPO over time. The results are shown in Table 1.

Table 1

Example	Additive	Amount added (resulting concentration)	Initial DMBAPO Conc. (%)	DMBAPO Conc (%). Time 1	DMBAPO Conc (%). Time 2
4*	DiMA	.02%wt or 0.004M	0.4	0.39 (42hr)	0.38 (70hr)
5*	DiMa	.103%wt or 0.023M	0.4	0.36 (48hr)	0.36 (69hr)
6	DCAA	.244%wt or 0.019M	0.4	0.40 (42hr)	0.40 (70hr)
7	HCl	0.1% or 0.01M	0.2	0.2 (40hr)	
8*	TBAH	.062M	0.2	0.04 (40hr)	

\*Comparative, not according to the invention.

DiMA=dimethylamine

15 DCAA=dichloroacetic acid

TBAH=tetrabutylammonium hydroxide

HCl= concentrated hydrochloric acid (37 %wt or 10.15M)

**Example 9-17 (Stability Studies in the Presence of Macromer)**

Solutions containing 10 %wt of the macromer described in example 1, 0.1 %wt of DMBAPO and various concentrations of acids, shown in Table 2, were prepared in 2-propanol. Samples were incubated at room temperature.

5

Table 2.

Example	Additive	Additive Conc. (resulting concentration)	Initial DMBAPO Conc (%).	DMBAPO Conc. At __ hrs (%)	DMBAPO Conc. At __ hrs (%)
10	No additive	N/A	0.11	0.094 (26.8hr)	0.063 (122hr)
11	HCl	0.01% or 0.001M	0.13	0.088 (27.3hr)	0.067 (122hr)
12	HCl	0.02% or 0.002M	0.13	0.126 (27.87hr)	0.097 (122hr)
13	HCl	0.05% or 0.005M	0.13	0.116 (28.38hr)	0.109 (122hr)
14	HCl	0.1% or 0.01M	0.092	0.093 (36.75hr)	0.088 (122hr)
15	HOAc	0.1% or 0.017M	0.135	0.132 (29.43hr)	0.106 (122hr)
16	HOAc	0.2% or 0.033M	0.107	0.099 (29.95hr)	0.09 (122hr)
17	HOAc	0.5% or 0.083M	0.161	0.066 (30.47hr)	0.154 (122hr)
18	HOAc	1.0% or 0.167M	0.108	0.112 (53.4hr)	0.106 (122hr)

HOAc=glacial acetic acid

10

Example 19-

Using the procedure of Examples 10-18, but storing at 45°C, the results shown in Table 3 were obtained.

5      Table 3

Example	Additive	Additive Conc. (resulting concentration)	Initial DMBAPO Conc. (%)	DMBAPO Conc at Time 1	DMBAPO Conc at Time 2
19	No additive	N/A	0.101	0.038 (50.88hr)	0.022 (120hr)
20	HCl	0.005	0.131	0.115 (50.88hr)	0.100 (120hr)
21	HCl	0.01M	0.143	0.129 (50.88hr)	0.116 (120hr)
22	HOAc	0.083M	0.113	0.0933 (50.88hr)	0.076 (120hr)
23	HOAc	0.167M	0.144	0.126 (50.88hr)	0.113 (120hr)

Example 24 (Stability studies of DMBAPO in monomer mix containing  
10      macromer)

Three monomer mixes of the type described in Example 2 (Lens formation)  
were prepared. Mix 1 contained no acid addition, Mix 2 contained 0.1 %wt  
concentrated HCl (37 %wt or 10.15M) and Mix 3 contained 1.0 %wt glacial acetic  
acid. Samples were incubated at 45°C and analyzed by Reversed-phase high  
15      performance liquid chromatography with Uv-Vis detection, to determine the  
presence of DMBAPO over time. The results are shown in Table 3.



Table 3

Example	Additive	Additive Conc. (resulting concentration)	Initial DMBAPO Conc. (%)	DMBAPO Conc at Time 1	DMBAPO Conc at Time 2
Mix 1	No acid (Mix 1)	N/A	0.339	0.144 (23hr)	0.044 (74.25hr)
Mix 2	HCl (Mix 2)	0.1%	0.374	0.348 (23hr)	0.280 (74.25hr)
Mix 3	HOAc (Mix 3)	1.0%	0.399	0.370 (23hr)	0.288 (74.25hr)

It was also found that maintaining the pH of the initiator solution between about 3 and 8 resulted in stability of the DMBAPO.

5

10

15

## CLAIMS

We claim:


5

1. A silicone hydrogel monomer formulation made by admixing:

a) a silicone hydrogel forming mixture,

10


b) an initiator having the structure:



Structure I

15

wherein, R<sup>1</sup>, R<sup>2</sup>, and R<sup>3</sup> are each independently H or a C<sub>1-12</sub> substituted or unsubstituted alkyl, cycloalkyl, or aromatic moiety provided that at least one of R<sup>1</sup>, R<sup>2</sup> and R<sup>3</sup> has the following structure:




20

Structure II

wherein,  $R^4$ - $R^8$  are independently, H or a  $C_{1-3}$  substituted or unsubstituted alkyl or alkoxy moiety; and


5 c) an acid.

2. The formulation of claim 1 wherein said acid is selected from the group consisting of Brønsted acids, Lewis acids, and mixtures thereof.
- 10 3. The formulation of claim 1 wherein said acid is a weak organic acid.
4. The formulation of claim 1 wherein said acid is acetic acid.
5. The formulation of claim 1 comprising 1 to 100 equivalents of acid per mole of  
15 initiator.
6. The formulation of claim 1 wherein said acid is an inorganic acid.
7. A method of stabilizing an initiator system comprising the step of lowering the  
20 pH of said system wherein the initiator system includes a compound having the structure:



Structure I

- 25 wherein,  $R^1$ ,  $R^2$ , and  $R^3$  are each independently H or a  $C_{1-12}$  substituted or unsubstituted alkyl, cycloalkyl, or aromatic moiety provided that at least one of  $R^1$ ,  $R^2$  and  $R^3$  has the following structure:




## Structure II

5


wherein, R<sup>4</sup>-R<sup>8</sup> are independently, H or a C<sub>1-3</sub> substituted or unsubstituted alkyl or alkoxy moiety.

- 10 8. The process of claim 7 wherein the pH is lowered to no more than 8.
9. The process of claim 7 wherein the pH is lowered by the admixture of an acid.
10. The process of claim 7 wherein the pH is lowered by the admixture of a member
- 15 of the group consisting of Brønsted acids, Lewis acids, and mixtures thereof.
11. The process of claim 7 wherein 0.1 to 10 weight % acid are admixed with said monomer mix containing initiator system.
- 20 12. A process for stabilizing a silicone hydrogel monomer formulation comprising an admixture of a reactive silicone macromer and a photoinitiator having the structure:



## Structure I

wherein,  $R^1$ ,  $R^2$ , and  $R^3$  are each independently H or a  $C_{1-12}$  substituted or unsubstituted alkyl, cycloalkyl, or aromatic moiety  
 5 provided that at least one of  $R^1$ ,  $R^2$  and  $R^3$  has the following structure:



## Structure II

10 wherein,  $R^4$ - $R^8$  are independently, H or a  $C_{1-3}$  substituted or unsubstituted alkyl or alkoxy moiety;

said process comprising the step of admixing an acid therewith.

15

13. The process of claim 12 wherein 0.1 to 10 weight % acid are admixed with said monomer mix containing initiator system and macromer.

20

14. The process of claim 12 wherein said acid is selected from the group consisting of Brønsted acids, Lewis acids, and mixtures thereof.

15. The process of claim 12 wherein said acid is a weak organic acid.

16. The process of claim 12 wherein said acid is acetic acid.

25

17. The process of claim 12 wherein said acid comprises a solution of at least .25%wt acetic acid.

